

SUMITUBE A

■ 規格 Specification values

性能Property	典型值 Typical value
物理特性：physical	
抗張強度(kg/mm ²)Tensile Strength	1.0min
伸長率(%)Elongation	200min
比重Specific gravity	0.92
吸水率(%)Water absorption	0.1max
縱向收縮率(%)Longitudinal shrinkage	15max
電氣特性:Electrical	
耐電壓(KV) Dielectric strength	2.5min
體積固有電阻(Ω-cm) Volume resistivity	10 ¹⁶ Ω-cm

勝特力材料 886-3-5753170
 勝特力电子(上海) 86-21-54151736
 勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)

公稱尺寸 Nominal size	收縮前 As supplied (mm.)		收縮後 After shrinkage (mm)		標準長度 Stand length (m)
	內徑 (D) Inside diameter	厚度 (Nominal) Wall thickness	內徑 (d) max Inside diameter	厚度(W)min Wall thickness	卷裝品 Spool
1.0×0.2	1.3±0.3	0.2	0.6	0.4±0.1	100
1.5×0.2	2.1±0.3	0.2	0.8	0.4±0.1	100
2×0.2	2.6±0.3	0.2	1.3	0.4±0.1	200
2.5×0.2	3.1±0.3	0.2	1.5	0.4±0.1	200
3×0.2	3.6±0.3	0.2	1.8	0.4±0.1	200
3.5×0.2	4.1±0.3	0.2	2.0	0.4±0.1	200
4×0.2	4.6±0.3	0.2	2.3	0.4±0.1	200
5×0.2	5.6±0.3	0.2	2.9	0.4±0.1	100
6×0.25	6.5±0.3	0.25	3.5	0.5±0.1	100
7×0.25	7.5±0.3	0.25	4.2	0.5±0.1	50
8×0.25	8.5±0.3	0.25	4.7	0.5±0.1	50
9×0.25	9.5±0.4	0.25	5.4	0.5±0.1	50
10×0.25	10.5±0.4	0.25	6.0	0.5±0.1	50
11×0.25	11.5±0.4	0.25	7.0	0.5±0.1	50
12×0.3	12.4±0.4	0.3	7.6	0.6±0.1	50
13×0.3	13.4±0.4	0.3	8.0	0.6±0.1	50

15×0.3	15.4±0.4	0.3	10.0	0.6±0.1	50
16×0.3	16.4±0.4	0.3	10.5	0.6±0.1	50
18×0.3	18.4±0.4	0.3	11.5	0.6±0.1	50
20×0.3	20.4±0.4	0.3	13.0	0.6±0.1	50
22×0.3	22.4±0.4	0.3	14.0	0.6±0.1	50
25×0.3	25.5±0.5	0.3	15.0	0.6±0.1	50

黑、棕、紅、橙、黃、綠、藍、紫、灰、白、透明

black/brown/red/orange/yellow/green/blue/violet/grey/white/clear

勝特力材料 886-3-5753170
 胜特力电子(上海) 86-21-54151736
 胜特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)